

# ADMIX GROUT II

NON-SHRINK, FREE FLOWING, SELF LEVELLING, ULTRA HIGH STRENGTH  
CEMENTITIOUS GROUT

---

## PRODUCT

Single pack ready to use, non-shrink, free flowing, self levelling, ultra high strength, cementitious grout designed with a blend of specially processed cement and fillers, with out corrosive substances.

## BENEFITS

Non-shrink characteristics, retain original volume by expansion. Free flowing, self-levelling grout easily filling under-bases of machinery. Pre packed batches ensure consistent material and only addition of water required at site. Excellent adhesion to concrete and steel. Non-metallic & chloride free.

## USES

Bolt pockets and base plate grouting of all equipments. Grouting of stanchion bases of all types of machinery with dynamic load in industries or industrial projects.

## DESCRIPTION

ADMIX GROUT II is based on specially processed cement, fillers and additives. It is ready to use component and only addition of water required at site. 25 kg ADMIX GROUT II requires 4.5 ltr of water for pourable and 4.75 ltr for flowing grout. Water powder (w/p) ratio is 0.18 and 0.19 respectively. ADMIX GROUT II is suitable for thickness between 10mm to 50mm. However in excess of 50mm thickness, cleaned and washed 10mm aggregate can be incorporated to the mix at the rate of 50% to 100% of the quantity of grout used. Controlled expansion takes place in the unset material to ensure that the grout, when cured, will continue to occupy its original volume. For thicker section it is necessary to incorporate well graded and washed aggregate in to the grout to minimise heat build up.

## STRENGTH DEVELOPMENT

The compressive strength development of ADMIX GROUT II, generally found to be as follows:

<u>AGE IN DAYS</u>	<u>COMPRESSIVE STRENGTH IN kg/cm<sup>2</sup></u>	
	<u>Pourable W/P 0.17</u>	<u>Flowable W/P 0.19</u>
1	300	250
3	375	350
7	500	450
28	700	650

-----  
7.07cm x 7.07cm size restrained cubes were tested

## PRODUCT PROPERTIES

Yield per 25 kg : 12.5 ltr approx.

Pourable life : 15 minutes max.

Application: 10°C to 40°C, Expansion (% Vol) 0.8 to 1.5,

Flow on flow table : 17 to 22cms.

## PACKING

Available in 25 kg HDPE bags.

## SHELF LIFE

Minimum 6 months from the date of manufacturing if stored in original container under shade, unopened.

## QUALITY ASSURANCES

ADMIX GROUT II is manufactured under stringent quality control and compatible with different climates of India.



No. 41, CCI House, 7<sup>th</sup> B Jakkur Cross, Opp: St.John's School, Amruthahalli, BANGALORE 560 092. Phone: (080) 23626333/ 23622421. Telefax (080)23622421.

Email : [sales@cciinc.in](mailto:sales@cciinc.in) - [info@cciinc.in](mailto:info@cciinc.in) Website: [www.cciinc.in](http://www.cciinc.in)

---

The information given in this data sheet is based on both current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we can not accept responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being under taken in our laboratory, we advise customers in their own interest to ensure that this data has not been superseded by a more up-to-date publication. Field services where provided, does not constitute supervisory responsibility. For additional information, CCI Inc local representative may be contacted.

---

