

LEAKGUARD-C SUPER

TWO PART ACRYLIC POLYMER MODIFIED (STYRENE ACRYLIC BASED)
CEMENTITIOUS WATERPROOF COATING SYSTEM

PRODUCT

Two part (powder + liquid – high density), pre-packed, acrylic polymer modified (styrene acrylic based) cementitious waterproof coating.

BENEFITS

Pre-packed product to ensure perfect proportion of mixing, excellent waterproofing characteristics, excellent adhesion, flexible layer, cost effective waterproofing system.

PACKING

LEAKGUARD-C SUPER is packed in two separate components in 9 kg powder and 5 ltr liquid of high density.

USES

All concrete structures like Roof tops, basements, water tanks, sunken slabs, swimming pools, retaining walls, slope roofs etc. LEAKGUARD-C SUPER can also be used for coatings on asbestos sheets and those areas where large section coating is required.

MIXING

LEAKGUARD-C SUPER should preferably be mixed mechanically to ensure uniform mixing for better cohesive consistency. Take out the liquid portion of LEAKGUARD-C SUPER to a bucket and slowly add powder portion while mixing is on. Mix it thoroughly till a homogenous paint consistency is formed.

Mixed LEAKGUARD-C SUPER should be used/consumed within 10 to 15 minutes. (max).

COVERAGE

LEAKGUARD-C SUPER gives a coverage of above 150 sft per pack, double coat. (5Ltr liquid of high density and 9 kg powder.)

SHELF LIFE

LEAKGUARD-C SUPER can be stored in original sealed pack under shade in dry condition for 12 months.

APPLICATION PROCEDURE

Surface preparation :

Surface should be cleaned thoroughly by using wire brush and all loose particles, oil stains if any, dust, paint etc., should be removed and cleaned by sufficient quantity of water. Un-plastered, un-even surfaces or any cracks on the surface should be repaired to make it even for better bonding. Surface should be strong & sound.

Application :

The prepared surface should be sufficiently wet and water stagnation if any, should be removed. Then mixed LEAKGUARD-C SUPER to be applied uniformly by brush both vertical and horizontal directions, one by one. Two or three coats are recommended.

ADDITIONAL INFORMATION

One extra coat of LEAKGUARD-C SUPER is recommended on the junctions and joints especially parapet wall bottom joints on rooftops. Slight water sprinkling on the first coat is recommended before starting second and subsequent coats.

WATER CURING

Light sprinkling of water for 2 to 3 times on LEAKGUARD-C SUPER applied surface for the first day will benefit into added advantage.

QUALITY ASSURANCES

LEAKGUARD-C SUPER is manufactured under stringent quality control and compatible with different climates of India.



No. 41, CCI House, 7th B Jakkur Cross, Opp: St.John's School, Amruthahalli, BANGALORE 560 092. Phone: (080) 23626333 / 23622421. Telefax. (080) 23622421.

website: www.cciinc.in Email: sales@cciinc.in info@cciinc.in

The information given in this data sheet is based on both current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we can not accept responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being under taken in our laboratory, we advise customers in their own interest to ensure that this data has not been superseded by a more up-to-date publication. Field services where provided, does not constitute supervisory responsibility. For additional information, CCI Inc local representative may be contacted.
